

DURAVIN™

THERMOPLASTIC COATINGS

DURAVIN™ is a multipurpose, fluidized-bed grade PVC thermoplastic powder coating formulated to meet the performance requirements of indoor, outdoor, and appliance applications while delivering the maximum economic benefits. To minimize environmental impact, DURAVIN™ powders are available in low-smoke technology for processing purposes. DURAVIN™ can be formulated for enhanced flexibility and hardness.



OVERVIEW

PVC Thermoplastic Coatings.

DURAVIN™ demonstrate remarkable resistance to long-term exposure to salt spray, UV and chemicals. Correctly applied with a liquid primer, DURAVIN™ thermoplastic powder coatings on a pre-treated substrate show excellent salt spray resistance, with no effects after 500 hours of

exposure and minimal undercutting after 1,000 hours. The product features high film strength, elasticity, and surface hardness, and can be customized in colors and finishes that meet specific application needs.

MAIN FEATURES

- **Excellent Corrosion Resistance** - Forms a durable barrier against moisture, chemicals, and environmental exposure.
- **Chemical Resistance** - Resists acids, salts, alkalis, and many industrial solvents.
- **High Flexibility** - Withstands bending and impact without cracking—ideal for dynamic or moving parts.
- **Two-Coat System** - Typically applied in a primer-plus-topcoat structure for enhanced durability and adhesion.
- **Available in Multiple Colors and Finishes** - Customizable appearance for branding, safety coding, or aesthetic needs.

APPLICATIONS

- **Wire Goods and Storage Systems** – Wire shelves, baskets, display racks
- **Fencing and Outdoor Structures** – Chain link fence wire, fence post and accessories
- **Appliance Components** – Dishwasher baskets
- **Automotive and Transportation** – Battery trays, seat frames and coils
- **Agricultural and Livestock Equipment** – Animal cages, feed bins, enclosure fencing



DURAVIN™

TECHNICAL PROPERTIES

Essential technical details are outlined below. Full Technical Data Sheet (TDS) available upon request.

TYPE	METHOD	RESULT
RECOMMENDED THICKNESS	ASTM D6132	8 mils (203 micron) - 12 mils (305 micron)
GLOSS	ASTM D523	70 ± 5
HARDNESS	ASTM D2240	Shore A 85+2
TENSILE STRENGTH	ASTM D638	2600 psi (18 MPa)
ELONGATION (%)	ASTM D638	180%
BRITTLINESS TEMPERATURE		-4 °F (-20 °C)
FLEXIBILITY	ASTM D522	1/8 in (3.2 mm), no cracks (>32%) (Conical Mandrel)
SALT SPRAY	ASTM B117	2000 hrs. No significant under cut or creep
QUV	ASTM G53	2000 hrs, no significant change in color or gloss.
HUMIDITY RESISTANCE	ASTM D2247	No blistering or loss of gloss after 1000 hours.
SPECIFIC GRAVITY OF FUSED FILM		1.30 ± 0.02
COVERAGE, LB/PER FT ² @ 10 MILS		0.07 ± 0.005
MELTING RANGE		395 – 415°F

SOLUTIONS

The Protech Group provides functional PVC coating solutions engineered to meet the performance demands of various industries and applications. Whether it's for wire products, fencing, appliances, automotive parts, or industrial equipment, our coatings deliver reliable protection, chemical resistance, and long-term durability tailored to your specific needs.

SUPPORT

To ensure the life of your asset is maximized, a simple and regular maintenance program should be implemented.

At The Protech Group, we prioritize your satisfaction and success. That's why we offer free support, even when challenges arise. From cleaning and phosphating all the way to the final cured film appearance, our experts are dedicated to assisting you every step of the way with proven solutions you can trust.

FORMULATING THE RIGHT MIX.

Since 1976, the Protech Group has been developing and manufacturing coatings, paints, and specialty materials. Through quality and innovation, we formulate the right mix to protect and enhance what matters most to our customers. Protech Group products are manufactured in more than 20 sites worldwide. We serve our customers in countless markets and industries, including construction, infrastructure, transportation, consumer goods, and healthcare.



info@theprotechgroup.com
www.theprotechgroup.com
1-800-361-9364



This document contains general information only and should not be construed as creating any warranties, expressed or implied.
© 2025 Protech Chemicals Inc. All rights reserved.